




|                     |   |
|---------------------|---|
| Fabric Name         | Oxford-110  |
| Fabric Weight       | 110gsm ±3%  |
| Composition         | 100% Polyester  |
| Full Width          | 150cm   |
| Weave               | 1/1 Plain   |
| Finishes            | -   |
| Area of use         | light workwear jackets<br>and rain coats  |
| Washing Instruction |  |

## PHYSICAL PROPERTIES

|   |   |                  | WARP             | WEFT |  |
|---|---|------------------|------------------|------|--|
| 1 | Tensile strength, N   | ISO 13934-1:2013 | 2700             | 2600 |  |
| 2 | Tearing strength, N   | ISO 13937-3:2000 | 80               | 65   |  |
| 3 | Dimensional Stability To Washing, max.                      | ISO 6330:2000    | 3.0%             | 3.0% |  |
| 4 | Abrasion Resistance   | ISO 12947-2:2002 | > 10 000         |      |  |
| 5 | Pilling Resistance  | ISO 12945-2:2000 | 3-4              |      |  |
| 6 | Colour Fastness To Washing<br>(cotton+polyester) 60°C, min. | ISO 105-C06:2010 |                  |      |  |
|   |   | Colour change    | ISO 105-C06:2010 | 4-5  |  |
|   |   | Colour staining  | ISO 105-C06:2010 | 4    |  |
| 7 | Colour Fastness To Perspiration, min.                       | ISO 105-E04:2013 |                  |      |  |
|   |   | Colour change    | 4-5              |      |  |
|   |   | Colour staining  | 4-5              |      |  |
| 8 | Colour Fastness To Rubbing, min.                            | ISO 105-X12:2001 |                  |      |  |
|   |   | Dry              | 4-5              |      |  |
|   |   | Wet              | 3-4              |      |  |
| 9 | Colour Fastness To Light                                    | ISO 105-B02:2013 | > 4              |      |  |